



# 广州市好印新材料科技有限公司

Guangzhou Haoyin New Material Technology Co., Ltd.

## RD-8715A Cold Peel Digital Printing DTF Film

### APPROVAL PAGE

Document Date: January 03, 2026

### TABLE OF CONTENTS

#### I. Product Features & Applications

#### II. Technical Parameters

#### III. Specifications & Packaging

#### IV. Storage & Shelf Life

#### V. Precautions

1、 Publishing Platform: DingTalk

2、 Authorized Access: All staff; Download permission: Department supervisors and above

3、 Implementation & Training: Business Department

4、 Revision Conditions:

A. Process changes; B. Material changes; C. Personnel changes in three-level approval positions

5、 Original Document Archive: General Office Archives

Prepared by: Li Jiexiang                      Development Department III                      Date: 2026-01-03

Reviewed by: Li Jiexiang                      Marketing Department                      Date: 2026-01-03

Approved by: Xu Qinghai                      CEO or Authorized Person                      Date: 2026-01-03



# 广州市好印新材料科技有限公司

Guangzhou Haoyin New Material Technology Co., Ltd.

## RD-8715A Cold Peel Digital Printing DTF Film

TDS--Product Application Information

### I. Product Features & Applications

- 1、Benefits: Excellent product stability, simple operation, effectively reduces waste rate.
- 2、Characteristics: Premium PET substrate with multi-coating process, single-side matte finish.
- 3、Advantages: Vibrant colors, high pattern precision, excellent powder removal.
- 4、Applications: More suitable for fine lines or pattern applications, such as wash care labels, mesh fabric, and fabrics with coarse warp and weft threads.
- 5、Limitations: Do not suggest hot peeled and peeling immediately. Pay attention to hot melt powder selection when adapting to different fabrics or substrates

### II. Technical Parameters

Test Item	Method/Equipment	Unit	Standard Value
Glossiness	Gloss Meter	Gu	6~10
Print Surface Resistance	High Resistance Tester	$\Omega/\square$	$10^6\sim 10^{11}$
Ink Absorption	Four-head Printer	Percentage of white ink	$\geq 85\%$ , no ink bleeding or pooling
Powder Shaking Effect	Visual Inspection	/	No powder adhesion on pattern edges and blank areas
Pattern Appearance	Visual Inspection	/	Vibrant and pure colors, good color saturation, no snowflake spots
Heat Transfer Effect	Visual Inspection	/	Cold peel, No coating transfer failure or chipping.

Operating Conditions Guide:

- 1、Heat Press Conditions: Temperature 130-150°C, Time 5-8s, Pressure 2.5 kgf/cm<sup>2</sup>.
- 2、Printing Parameters: Feed section(In/Out) temperature 40~45°C, oven front heat plate 70~80°C.
- 3、Curing Conditions: Curing temperature 135°C~145°C. Adjustable within range based on actual print speed. Ensure exhaust system is operating properly.

*Above data obtained under laboratory test conditions for reference only.*

Address: Room.309, No.9 Shenzhou Road, Huangpu District, Guangzhou, Guangdong Province, China.  
Hotline: 020-31701916  
gzhayin.com

Email: info@gzhaoyin.com  
Postal Code: 510663



# 广州市好印新材料科技有限公司

Guangzhou Haoyin New Material Technology Co., Ltd.

## III. Specifications & Packaging

Standard stock: Width 60 cm × Length 100 m/roll, 60 m<sup>2</sup>/roll/2 boxes/carton. Custom specifications available upon request.

## IV. Storage & Shelf Life

- 1、 Store in a cool, dry place protect from direct sunlight, high temperatures (above 40° C) and high humidity (above 70% RH).
- 2、 Prevent contact with sharp objects. Close lid tightly after opening to prevent exposure to air and contaminants.
- 3、 Shelf life: 12 months under proper packaging and storage conditions. Verify product performance after expiration date before use.

## V. Precautions

- 1、 Product data provided for reference only. Users should conduct thorough validation and evaluation of product suitability for specific applications (purpose and conditions) prior to use.
- 2、 In no event shall QINGYI be liable for any incidental or consequential damages.

Address: Room.309, No.9 Shenzhou Road, Huangpu District, Guangzhou, Guangdong Province, China.  
Hotline: 020-31701916  
gzhayin.com

Email: info@gzhayin.com  
Postal Code: 510663