



# 广州市好印新材料科技有限公司

Guangzhou Haoyin New Material Technology Co., Ltd.

RD-8716B Warm/Cold Peel DTF Film

## APPROVAL PAGE

Document Date: January 03, 2026

### TABLE OF CONTENTS

#### I. Product Features & Applications

#### II. Technical Parameters

#### III. Specifications & Packaging

#### IV. Storage & Shelf Life

#### V. Precautions

- 1、 Publishing Platform: DingTalk
- 2、 Authorized Access: All staff; Download permission: Department supervisors and above
- 3、 Implementation & Training: Business Department
- 4、 Revision Conditions:
  - A. Process changes; B. Material changes; C. Personnel changes in three-level approval positions
- 5、 Original Document Archive: General Office Archives

Prepared by: <u>Li Jiexiang</u>	Development Department III	Date: <u>2026-01-03</u>
Reviewed by: <u>Li Jiexiang</u>	Marketing Department	Date: <u>2026-01-03</u>
Approved by: <u>Xu Qinghai</u>	CEO or Authorized Person	Date: <u>2026-01-03</u>



# 广州市好印新材料科技有限公司

Guangzhou Haoyin New Material Technology Co., Ltd.

## RD-8716B Warm/Cold Peel DTF Film

TDS--Product Application Information

### I. Product Features & Applications

- 1、Benefits: Excellent product stability with wide operational adaptability.
- 2、Characteristics: Premium PET substrate with multi-coating process, double-side matte finish.
- 3、Advantages: Vibrant colors, high pattern precision, excellent powder removal, paper feeding without slipping, anti-blocking effect on back side.
- 4、Applications: Suitable for irregular large pattern applications. Standard DTF white ink heat transfer film.
- 5、Limitations: Do not suggest peeling immediately. Allow to cool for 5-8 seconds before peeling. Pay attention to hot melt powder selection when adapting to different fabrics or substrates.

### II. Technical Parameters

Test Item	Method/Equipment	Unit	Standard Value
Glossiness	Gloss Meter	Gu	3~9
Print Surface Resistance	High Resistance Tester	$\Omega/\square$	$10^6\sim 10^{11}$
Ink Absorption	Four-head Printer	Percentage of White Ink	$\geq 85\%$ , no ink bleeding or pooling
Powder Shaking Effect	Visual Inspection	/	No powder adhesion on pattern edges and blank areas
Pattern Appearance	Visual Inspection	/	Vibrant and pure colors, good color saturation, no snowflake spots
Heat Transfer Effect	Visual Inspection	/	Warm peel (5-8 seconds), No coating transfer failure or chipping.

#### Operating Conditions Guide:

- 1、Heat Press Conditions: Temperature 130-150°C, Time 5-8s, Pressure 2.5 kgf/cm<sup>2</sup>.
  - 2、Printing Parameters: Feed Section(In/Out) temperature 40~45°C, Pre-oven heating plate 70~80°C.
  - 3、Curing Conditions: Curing temperature 135°C~145°C. Adjustable within range based on actual print speed. Ensure exhaust system is operating properly.
- Above data obtained under laboratory test conditions for reference only.

Address: Room.309, No.9 Shenzhou Road, Huangpu District, Guangzhou, Guangdong Province, China.  
Hotline: 020-31701916  
gzhaoyin.com

Email: info@gzhaoyin.com  
Postal Code: 510663



广州市好印新材料科技有限公司

Guangzhou Haoyin New Material Technology Co., Ltd.

### III. Specifications & Packaging

Standard stock: Width 60 cm × Length 100 m/roll, 60 m<sup>2</sup>/roll/2 boxes/carton. Custom specifications available upon request.

### IV. Storage & Shelf Life

- 1、 Store in a cool, dry place protect from direct sunlight, high temperatures (above 40° C) and high humidity (above 70% RH).
- 2、 Prevent contact with sharp objects. Close lid tightly after opening to prevent exposure to air and contaminants.
- 3、 Shelf life: 12 months under proper packaging and storage conditions. Verify product performance after expiration date before use.

### V. Precautions

- 1、 Product data provided for reference only. Users should conduct thorough validation and evaluation of product suitability for specific applications (purpose and conditions) prior to use.
- 2、 In no event shall QINGYI be liable for any incidental or consequential damages.

Address: Room.309, No.9 Shenzhou Road, Huangpu District, Guangzhou, Guangdong Province, China.  
Hotline: 020-31701916  
gzhayin.com

Email: info@gzhayin.com  
Postal Code: 510663