



广州市好印新材料科技有限公司

Guangzhou Haoyin New Material Technology Co., Ltd.

QJ02 Series Glitter Heat Transfer Vinyl

APPROVAL PAGE

Document Date: January 3, 2026

TABLE OF CONTENTS

I. Product Features & Applications

II. Technical Parameters

III. Specifications & Packaging

IV. Storage & Shelf Life

V. Precautions

1、 Publishing Platform: DingTalk

2、 Authorized Access: All staff; Download permission: Department supervisors and above

3、 Implementation & Training: Business Department

4、 Revision Conditions:

A. Process changes; B. Material changes; C. Personnel changes in three-level approval positions

5、 Original Document Archive: General Office Archives

Prepared by: Zhou Zhihong Manufacturing Center Date: 2026-01-03

Reviewed by: Li Jiexiang Marketing Department Date: 2026-01-03

Approved by: Xu Qinghai CEO or Authorized Person Date: 2026-01-03



广州市好印新材料科技有限公司

Guangzhou Haoyin New Material Technology Co., Ltd.

QJ02 Series Glitter Heat Transfer Vinyl

TDS--Product Application Information

I. Product Features & Applications

- 1、Benefits: Sparkling appearance with distinctive strong rough texture. Glitter powder resistant to falling off during washing, excellent fastness, colorfast.
- 2、Characteristics: PET glitter powder, high temperature resistant, multiple color codes available, various colors to choose from, customizable.
- 3、Advantages: Adhesive-type high-tack positioning film for easy cutting, easy weeding, and re-tack capability.
- 4、Applications: Suitable for textile fabrics and leather. Compatible with laser cutter or cold blade vinyl cutters.
- 5、Limitations: Slight glitter powder loss during heat transfer is normal and does not affect performance. Not suitable for fine line pattern processing.

II. Technical Parameters

Item	Method/Equipment	Unit	Standard Value
Effective Thickness	Digital Thickness Gauge	μm	270~390
Washing ①	4A Standard (50°C water/60 min/cycle)	/	+++
Color Difference (Same Batch)	Handheld Spectrodensitometer	/	ΔE≤6
Release Force (Before Heat Press)	internal	N/inch	0.3~3.0 实测范围
Peel Force (After Heat Press)		N/inch	0.5~5.0 实测范围

Notes:① One 4A wash cycle is equivalent to approximately 10 regular home washes. Three or more 4A wash cycles = (+++); one 4A wash cycle = (+).

② Recommended heat press parameters: Temperature 145~160° C × Time 12~16 s × Pressure 0.3 MPa. Conduct relevant tests after 24 hours at room temperature following heat pressing.

III. Specifications & Packaging

Standard stock size: 61 cm × 25 m. Other custom specifications available upon request.

IV. Storage & Shelf Life

- 1、Store in a cool, dry place away from direct sunlight. Avoid high temperatures (above 40° C) and high humidity (above 70% RH).
- 2、Prevent contact with sharp objects. Reseal unused portions after opening.
- 3、Shelf life: 12 months under proper packaging and storage conditions. Verify product performance after expiration date before use.

Address: Room.309, No.9 Shenzhou Road, Huangpu District, Guangzhou, Guangdong Province, China.
Hotline: 020-31701916
gzhaoyin.com

Email: info@gzhaoyin.com
Postal Code: 510663



广州市好印新材料科技有限公司

Guangzhou Haoyin New Material Technology Co., Ltd.

V. Precautions

- 1、 Product data provided for reference only. Users should conduct thorough validation and evaluation of product suitability for specific applications (purpose and conditions) prior to use.
- 2、 For processes, materials, or equipment outside the specified product scope, preliminary testing or consultation with our sales team is recommended to achieve optimal product performance.
- 3、 This company disclaimer excludes liability for any incidental or consequential damages.

Address: Room.309, No.9 Shenzhou Road, Huangpu District, Guangzhou, Guangdong Province, China.
Hotline: 020-31701916
gzaoyin.com

Email: info@gzaoyin.com
Postal Code: 510663